

F&D

O'CONNOR PTY LTD

15 PELMET CRESCENT
THOMASTOWN VIC 3074
AUSTRALIA
P.O. BOX 2106
GREENVALE 3059

PHONE: (03) 9462 4544
FAX: (03) 9462 4744


A.C.N. 067 591 155 A.B.N. 24 067 591 155

EMAIL: belts@fdoconnor.com.au

SUPPLIERS OF CONVEYOR BELTING AND TRANSMISSION EQUIPMENT

DATA SHEET

Belt Type: TT123



Thickness (mm)	1.6		
Weight (kg/m²)	1.7		
Max Width (mm)	1950		
Min Pulley diameter	25		
Nosebar Diameter (mm)	N/A		
Minimum back flex	35		
Load for 1% elongation (N/mm)	6		
Max working Tension	12		
Op temp (min) deg	-40	Op temp (max) deg	100
Conveying side material	SILICON		
Conveying side colour	WHITE		
Underside Material	sc		
Underside feature	POLYURETHANE		
Underside colour	CLEAR		
Co- efficient of friction (u)	0.15		
Applications	Acceleration Belt, decline belt, incline belt, Bakery (cookie/biscuit), chocolate/confectionery, sweets/snacks/bars/chewing gum.		
Characteristics	Adhesive/easy- release, anti-sticking, super adhesive surface.		
Food approval	FDA/USDA		

Values shown are typical and are subject to change without notice. Before using, the user should determine the suitability of the product for its intended use and assumes all risk and liability in connection therewith. Specifications are subject to change without notice. Weight tolerance g/m² + or -5% variation, Teflon® content + or -2% variation.